

# Matrixcote<sup>®</sup> Concentrate

## Formulations

Due to the unique nature of the product, the formulation implemented will vary from foundry to foundry. This flexibility allows the foundry to obtain the maximum number of benefits from MATRIXCOTE concentrate.

For specific slurry formulations, please call our Technical Department at 800.800.7496 to discuss your specific application and to obtain the proper formulation to fit your needs.

## Application Recommendations

1. Remix the MATRIXCOTE concentrate prior to use to ensure a homogeneous blend of material.
2. For best results, weigh all ingredients when making up a new slurry or making additions to an existing slurry.
3. When building the slurry, add the refractory last. If more than one refractory is used, add the lowest density refractory first: fused silicas (2.2 g/cc), alumino silicates (2.7 g/cc), zircon (4.5 g/cc). Add refractory slowly for best results.
4. New and makeup slurries must be prepared with a propeller mixer, not in a rotating tank. This ensures proper dispersion of the refractory particles. The propeller mixer must be of adequate HP and RPM. Excessive mixing action can introduce air into the slurry and cause erratic viscosity and/or bubbles in the slurry coat.
5. As with any slurry, the viscosity of the slurry must be stable before use. A stable viscosity is one that does not change by more than 1 second when checked at 1 hour intervals. Viscosity can be increased by adding more refractory and decreased by adding more binder.
6. It is required to replace water lost to evaporation. When water is needed (based on test results for viscosity and/or binder solids), use distilled or deionized water as opposed to tap water, which can contain contaminants that can negatively affect slurry life.
7. Antifoam, wetting and bactericide agents are already formulated into MATRIXCOTE concentrate and other additions may not be compatible. Contact R&R's technical team before making these additions to the slurry.

## Slurry Control Procedures

Slurry Control Worksheets are available for download at [www.ransom-randolph.com](http://www.ransom-randolph.com) under resources. Slurry Control Worksheets allow you to input data directly and help you calculate values.



### RANSOM & RANDOLPH

Maumee, OH 43537 USA

Toll Free: 800.800.7496

Phone: 419.865.9497

Fax: 419.865.9997

[www.ransom-randolph.com](http://www.ransom-randolph.com)

Issue Date: 021617 / Replaces: 081116

*Investing with Innovation<sup>™</sup>*

# Matrixcote<sup>®</sup> Concentrate

## Slurry Testing Frequency

R&R recommends running the following tests accordingly.

Slurry Test	Recommended Testing Frequency
Slurry Viscosity	Two Times Per Shift
Slurry Density	Weekly
Refractory Solids	Weekly
Binder Solids	Two Times Per Week
Binder pH	Weekly

## Target Binder Solids Range

The target binder solids range for MATRIXCOTE concentrate is 25.5%-27.5% by weight.

Specific Gravity	Binder Solids	Specific Gravity	Binder Solids	Specific Gravity	Binder Solids
1.130	23.5	<b>1.145</b>	<b>25.5</b>	1.160	27.6
1.131	23.6	<b>1.146</b>	<b>25.7</b>	1.161	27.7
1.132	23.8	<b>1.147</b>	<b>25.8</b>	1.162	27.9
1.133	23.9	<b>1.148</b>	<b>26.0</b>	1.163	28.0
1.134	24.0	<b>1.149</b>	<b>26.1</b>	1.164	28.2
1.135	24.2	<b>1.150</b>	<b>26.2</b>	1.165	28.3
1.136	24.3	<b>1.151</b>	<b>26.4</b>	1.166	28.4
1.137	24.4	<b>1.152</b>	<b>26.5</b>	1.167	28.6
1.138	24.6	<b>1.153</b>	<b>26.6</b>	1.168	28.7
1.139	24.7	<b>1.154</b>	<b>26.8</b>	1.169	28.8
1.140	24.9	<b>1.155</b>	<b>26.9</b>	1.170	29.0
1.141	25.0	<b>1.156</b>	<b>27.1</b>	1.171	29.1
1.142	25.1	<b>1.157</b>	<b>27.2</b>	1.172	29.3
1.143	25.3	<b>1.158</b>	<b>27.3</b>	1.173	29.4
1.144	25.4	<b>1.159</b>	<b>27.5</b>	1.174	29.5



### RANSOM & RANDOLPH

Maumee, OH 43537 USA

Toll Free: 800.800.7496

Phone: 419.865.9497

Fax: 419.865.9997

www.ransom-randolph.com

Issue Date: 021617 / Replaces: 081116

*Investing with Innovation<sup>™</sup>*

# Matrixcote<sup>®</sup> Concentrate

## Safety

OSHA-approved respiratory protection should always be worn to avoid inhalation of respirable silica dust, which can result in an irreversible lung disease, silicosis. Such exposure includes slurry makeup, casting, knockout and cleanup. Refer to SDS for specific details.

## Storage & Handling

Keep from freezing. MATRIXCOTE concentrate must be maintained above 35 °F (2 °C) to prevent the material from precipitating irreversibly and making the product unsuitable for use. Binder stored in transparent or translucent containers should be sheltered from direct sunlight. Shelf life is 1 year from date (MMDDYY) in batch lot number on label. Rotate stock to maximize shelf life.

## Technical Tips

For additional information and recommendations, refer to the Shell Building, Slurry Control, Autoclaving and FlashFire Dewax Method Technical Tips available for download at [www.ransom-randolph.com](http://www.ransom-randolph.com) under resources.

*As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.*



### **RANSOM & RANDOLPH**

Maumee, OH 43537 USA

Toll Free: 800.800.7496

Phone: 419.865.9497

Fax: 419.865.9997

[www.ransom-randolph.com](http://www.ransom-randolph.com)

Issue Date: 021617 / Replaces: 081116

*Investing with Innovation™*