

Ceramic Pour Cups



Quality ceramic pour cups are an important part of the ceramic shell tree assembly. A well-manufactured cup can reduce the risk of casting defects resulting from cup erosion during a metal pour. The better the surface quality of the pour cup used, the less opportunity for cup erosion or spalling.

Schaefer Industries, Inc. ceramic pour cups provide the best possible quality to the investment caster. Every piece produced is 100% visually inspected at various points throughout the manufacturing process. Parts are rejected for the slightest flaw to ensure defect-free performance on the foundry floor.

Ceramic pour cups are sufficiently dense to resist the thermal shock that occurs when molten metal meets ceramic. Again, reducing the potential failure during a pour.

Ceramic pour cups are composed of clay-bonded mullite with a very low tramp element content to satisfy stringent aerospace specifications.

Component	Weight %
Alumina (Al ₂ O ₃)	50.0
Silica (SiO ₂)	47.0
Ferric Oxide (Fe ₂ O ₃)	0.6
Titania (TiO ₂)	1.0
Phosphorous Pentoxide (P ₂ O ₅)	0.1
Sodium Oxide (Na ₂ O)	0.1
Calcium Oxide (CaO)	0.2
Potassium Oxide (K ₂ O)	0.3
Magnesium Oxide (MgO)	0.2
Other	0.5

Other products are also available, including: alumina shapes and basins, rings, collars, cover plates, vent plugs and castable shapes.



RANSOM & RANDOLPH
Maumee, OH 43537 USA
Toll Free: 800.800.7496
Phone: 419.865.9497
Fax: 419.865.9997
www.ransom-randolph.com

Issue Date: 022317 / Replaces: 081816

PRODUCT DATA SHEET

Investing with Innovation™

Ceramic Pour Cups

Standard Ceramic Pour Cup Options

Part #	Neck Inner Diameter	Neck Outer Diameter	Large Inside Diameter	Large Outside Diameter	Height	Angle	Filter Diameter
SII-2FLE	1.25	1.75	3.00	3.75	2.50	37.00	
SII-1.375	1.38	1.90	3.08	3.50	3.00		
SII-2.3RO	2.05	2.68	6.50	7.13	2.75	40.00	
SII-2.6F	2.60	3.20	4.00	5.25	1.75	23.00	
SII2.75E	2.75	3.25	4.70	5.40	3.75	20.00	
SII-3	2.00	2.65	4.00	4.65	2.80		
SII-3F	2.00	2.65	4.00	5.25	2.80		
SII-3FIT	2.00	2.65	4.00	4.65	2.80		2.41
SII-3FL	2.00	2.50	4.20	5.00	3.00	20/30	
SII-3.5FIT	1.76	2.50	4.20	5.05	3.50		2.25
SII-3.75	2.50	3.13	4.63	5.25	3.00	20.00	
SII-3x3	3.00	3.50	4.00	4.50	3.00	10.00	
SII-3.8F	3.00	3.80	4.75	5.50	3.80	14.00	
SII-4	2.00	2.50	4.60	5.35	4.00		
SII-4FIT	2.00	2.65	4.60	5.35	4.00		2.50
SII-5F	2.40	2.92	4.60	5.90	4.25		
SII-6.3F	3.00	3.52	5.25	6.15	3.10		
SII-7.3	3.00	3.50	6.00	6.50	5.40		
SII-8FR*	2.50	3.13	6.00	7.00	4.25		

F = Flange

FL = Flare

FIT = Space for straight sided filter

*Anti-swirl ribs optional

Custom designed ceramic pour cups are also available. If you require a special design, contact your R&R Regional Manager or Customer Service Representative to request a quotation.

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.

PRODUCT DATA SHEET



RANSOM & RANDOLPH

Maumee, OH 43537 USA

Toll Free: 800.800.7496

Phone: 419.865.9497

Fax: 419.865.9997

www.ransom-randolph.com

Issue Date: 022317 / Replaces: 081816

Investing with Innovation™