

# Zircon

Zircon is a naturally occurring refractory mineral and is therefore subject to variability. It is chemically inert and is stable to very high temperatures. Zircon has a very high thermal conductivity and acts as a chill to eliminate metal mold reactions and burn-in, resulting in a smooth cast surface. Zircon is available in both granular and flour form.



Zircon is almost exclusively used in the primary slurry and as a primary stucco. Because of its high density, zircon provides excellent flow characteristics in a primary slurry. The round grains do not cause defects such as rough casting surfaces.

## Typical Material Properties\*

%	Sand	Flours
Zirconium Dioxide (ZrO <sub>2</sub> )	≥65.0%	≥65.0%
Silica (SiO <sub>2</sub> )	≤33.0	≤33.0
Alumina (Al <sub>2</sub> O <sub>3</sub> )	≤2.0	≤2.0
Titania (TiO <sub>2</sub> )	≤0.35	≤0.35
Ferric Oxide (Fe <sub>2</sub> O <sub>3</sub> )	≤0.05	≤0.05
Melting Point	4001 °F (2205 °C)	4001 °F (2205 °C)
Specific Gravity	4.5	4.5
Refractive Index	2	2
Hardness (Mohs)	7.5	7.5
Thermal Expansion Coefficient (cm/cm/°C)	4.2 x 10 <sup>-6</sup>	4.2 x 10 <sup>-6</sup>

\*Trebol USA has determined test method and provided analysis as noted herein. The levels referenced herein are only for general guidance and do not constitute a firm specification.

## PRODUCT DATA SHEET



**RANSOM & RANDOLPH**  
 Maumee, OH 43537 USA  
 Toll Free: 800.800.7496  
 Phone: 419.865.9497  
 Fax: 419.865.9997  
[www.ransom-randolph.com](http://www.ransom-randolph.com)

Dentsply  
Sirona

Issue Date: 022817 / Replaces: 082216

*Investing with Innovation™*

# Zircon

## Particle Size\*

### Zircon Sand

- 96-111 AFS

### Zircon Flours

	140 Mesh	200 Mesh	325 Mesh	400 Mesh
Particle Size (Microns) d 50%	40	20	14	10.5
Residue in 200 Mesh (%) maximum	10.0 - 20.0	0.5 - 3.0	—	—
Residue in 325 Mesh (%) maximum	—	—	0.5 - 6.0	—
Residue in 400 Mesh (%) maximum	—	—	—	1.0 - 6.0

\*Trebol USA has determined test method and provided analysis as noted herein. The levels referenced herein are only for general guidance and do not constitute a firm specification.

*As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.*

## PRODUCT DATA SHEET



### RANSOM & RANDOLPH

Maumee, OH 43537 USA

Toll Free: 800.800.7496

Phone: 419.865.9497

Fax: 419.865.9997

[www.ransom-randolph.com](http://www.ransom-randolph.com)

Issue Date: 022817 / Replaces: 082216

*Investing with Innovation™*