

R&R® ARGENTUM™ Investment

An economical Alternative for Casting Silver, Brass and Bronze



R&R ARGENTUM investment provides jewelry casters with an economical investment that reduces excess metal and watermarking defects for dependable casting results and maximum profits.

Available from Europe.

Typical Material Properties*

Water/Powder Ratio	38 parts water to 100 parts powder by weight
Water Temperature	72°F-73°F (22°C-23°C)
Working Time	11-11.5 minutes
Setting Time	<22 minutes
Slump	111mm - 117mm

*These results are based on the testing methods, frequency and procedures of Ransom & Randolph or its approved suppliers. The levels referenced herein are only for general guidance and do not constitute a firm specification.

PRODUCT DATA SHEET



RANSOM & RANDOLPH

Maumee, OH 43537 USA
Toll Free: 800.800.7496
Phone: 419.865.9497
Fax: 419.865.9997
www.ransom-randolph.com

Issue Date: 022717 / Replaces: 082316

Investing with Innovation™