# SUSPENDASLURRY® FS MATERIAL







#### Ready-to-Use Ceramic Shell Slurry

SuspendaSlurry FS material was developed to eliminate costs associated with continuous mixing and to simplify the initial mixing process as the pre-mixed, chemically suspended ceramic shell slurry eliminates the need to weigh and mix binder and refractory components.

Used for non-ferrous metals, SuspendaSlurry FS material is recommended for both initial and backup coats and is available in 60 pound (5 gallon) and 400 pound (30 gallon) slurries.

#### Simplify Slurry Makeup

SuspendaSlurry FS material is pre-mixed when it leaves the R&R manufacturing facility. The risk of operator error in adding the proper amounts of flour to a binder is eliminated, as are the labor time and costs associated with this step of the process. A standard slurry can take a day or more to wet-out before dipping can start. SuspendaSlurry FS material can be remixed in minutes, often by hand, and used immediately upon opening.

- Reduce expense and equipment maintenance no propeller mixers required to wet-out refractory.
- Reduce labor costs associated with weighing and mixing flour and binder components.
- Eliminate time wasted waiting for a slurry to wet-out.

#### **Eliminate Continuous Slurry Mixing**

Many foundries experience the costly loss of slurries when electric supply fails over a weekend. Others have experienced the loss of teardrop tanks and slurries when the propeller mixer moves off-center and cuts through the tank wall or when the propeller and shaft uncouple from the motor while the foundry is closed. SuspendaSlurry FS material is formulated to maintain suspension for months without mixing; allowing the foundry to turn off mixers and tanks entirely - eliminating the risk of slurry loss due to uncontrollable, off-hour failures.

- Save electricity and lower costs by turning tanks off when not in use.
- Eliminate the risk of slurry loss and costly replacement due to electrical failure or a damaged tank.

#### Simplify Slurry Maintenance

Slurry maintenance is simplified for the operator. Slurry viscosity is the only test parameter required to control the slurry. If viscosity is too high, a simple water adjustment will bring the slurry back into control. Placing a tight sealing lid on the slurry tank after dipping helps preserve water in the slurry so additions are required less frequently.

Reduce labor costs and time associated with intensive slurry testing.

#### **Proven Casting Performance**

SuspendaSlurry FS material is based on R&R's leading primary binder technology. This allows casters added benefits over standard colloidal silica shells. The primary coats of SuspendaSlurry FS material will result in stronger layers, reducing the potential for buckling, lifting or cracking defects. The slurry will flow, coat and drain in a fluid manner, eliminating any need for manual wax pattern application. SuspendaSlurry FS material also contains a color indicator. When the shell changes from yellow to orange, the shell is ready for another dip.



# RANSOM & RANDOLPH

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) www.ransom-randolph.com







### SUSPENDASLURRY® FS MATERIAL

#### Application Recommendations

- 1. Remix the SuspendaSlurry FS material prior to use to ensure a homogeneous blend of material. Remixing time will vary with the size of the slurry, but should take minutes. Small slurries may be remixed by hand, larger slurries may require a propeller mixer. Remix until the liquid at the top of the slurry is blended and the mixture is creamy in appearance.
- Remove the propeller mixer from the tank after initial remixing.
- Patterns must be clean and free from silicones or other contaminants before dipping.
- It is not usually necessary to use a prewet between coats. If a prewet is needed, use deionized water only. Drain the pattern before dipping into the slurry.
- 5. Once finished dipping shells, replace slurry tank lid to prevent evaporation.
- 6. When using SuspendaSlurry FS material again, remix to a creamy consistency prior to dipping if there is a visual separation of liquid at the top of the tank. If there is no separation visible, dip without remixing.

#### **Slurry Control Procedures**

- 1. SuspendaSlurry FS material requires simple viscosity control.
- 2. Control viscosity with water adjustments only. As the viscosity increases, add water to bring the slurry back into target viscosity range. Use distilled or deionized water as opposed to tap water; which can contain contaminants that can negatively affect slurry life.
- 3. Antifoam, wetting and bactericide agents are already formulated into SuspendaSlurry FS material and other additions may not be compatible. Contact R&R's technical team before making additions to the slurry.

#### Slurry Testing Frequency

R&R recommends running the following tests accordingly.

Slurry Test	Recommended Testing Frequency	Target Ranges
Total Solids	Weekly	70-72%
Slurry Viscosity	Start of each shift	#4 Signature Series Zahn Cup: 19-21 seconds #5 Signature Series Zahn Cup: 12-13 seconds

#### Refractory Loading

SuspendaSlurry FS material is provided at 60% fused silica. It is not recommended to use a different refractory load level.

#### Storage & Handling

Always keep SuspendaSlurry FS material sealed tightly when not in use to prevent evaporation. Protect from freezing. SuspendaSlurry FS material must be maintained above 35°F (2°C) to prevent the material from precipitating irreversibly and making the product unsuitable for use. Shelf life is 1 year from date (MMDDYY) in batch lot number on label. Rotate stock to maximize shelf life.

Once per month, whether dipping parts or not, open the container of SuspendaSlurry FS material, gently remix and reseal container lid. Settling will occur over time; if left for too long and unused, the settling process may be too difficult to reverse.

#### Safety

OSHA-approved respiratory protection should always be worn to avoid inhalation of respirable silica dust, which can result in an irreversible lung disease, silicosis. Such exposure includes shell building, casting, knockout and cleanup. See SDS for more information.

#### **Technical Tips**

For additional information and recommendations, refer to the Shell Building, Autoclaving and FlashFire Dewax Method Technical Tips available for download at www.ransom-randolph.com.



# RANSOM & RANDOLPH

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) www.ransom-randolph.com







### SUSPENDASLURRY® FS MATERIAL

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.



RANSOM & RANDOLPH

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) www.ransom-randolph.com







Issue Date: March 22, 2024