# 910 INVESTMENT CORE MATERIAL



#### A Calcium Sulfate Bonded Investment Used for Cores

It is used with non-ferrous alloys which do not exceed temperatures of 2200°F (1200°C).

910 investment core material has good green strength, good thermal shock resistance, is easily removed after casting and can be used directly in contact with the wax pattern.

#### Application Recommendations

Water/Powder Ratio by Weight*	Working Time	Setting Time
28/100	10-11 minutes	12-14 minutes

\*To improve the strength of 910 investment core material, replace a portion of the water with Core Hardener 2000™ binder. Flow characteristics are reduced when using higher percentages of Core Hardener 2000 binder. It is recommended to use 2 parts water to 1 part Core Hardener 2000 binder by volume.

- 1. Calcium sulfate bonded core materials require core pins to hold them in place. Place core pins through the wax until they protrude at least <sup>1</sup>/<sub>2</sub>" into the cavity to be cored. This distance will vary depending on the size of the core. They should extend about  $\frac{1}{2}$ " outside the wax so the shell can be built around them.
- Powder should be added to water in the proper proportions and mixed by hand or mechanically to make a smooth consistency.
- 3. Pour the core material into the cavity. Some vibration may be used to help fill the core easier and remove entrapped air. Allow the completed core to set 3-4 hours before further processing.
- 4. It is important to remember that when a complete-fill core material is used, you must allow extra time during dewaxing and burnout to completely dry and burn out the core. Failure to burn out the core completely may lead to outgassing when metal is poured.
- 5. Where autoclave dewaxing is used to remove the pattern, the pressure must be released very slowly to prevent destruction of the core material.
- Placing vents into the cores to help in drying and eliminating gases during casting is recommended. 6.

## Storage & Handling

Shelf life is 1 year from date (MMDDYY) in batch lot number on label. Rotate stock to maximize shelf life.

## Safety

North America: Danger. Contains crystalline silica. May cause cancer. Causes damage to lungs through prolonged or repeated exposure by inhalation. See SDS for more information

EU: Danger. Contains respirable crystalline silica. May cause damage to lungs through prolonged or repeated exposure. See SDS for more information.

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this product. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, expressed or implied, regarding accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state, and local regulations remains the responsibility of the user. All potential liability related to the sale and use of this product is limited to the cost of the particular goods sold in their respective transactions.



# **RANSOM & RANDOLPH**

3535 Briarfield Boulevard | Maumee, OH 43537 USA 800.800.7496 | 419.865.9497 | 419.865.9997 (FAX) www.ransom-randolph.com flin

Made in the USA

Issue Date: March 21, 2024

Ransom & Randolph GmbH Leipziger Straße 40 | 04571 Rötha Germany +49 342 06373999 Investing with Innovation™